

General product information

Elastollan® LP 9277

®= Registered Trademark of Elastogran GmbH

Elastogran



■ • BASF Group

Characteristic:

Aliphatic, light-fast thermoplastic Polyester-Polyurethane with excellent colour fastness, detailed reproduction of surface structures, resistance to hydrolysis and low fogging values. Processable by injection moulding and extrusion.

Property	Unit	Value	Test method according to
Hardness	Shore A	68	DIN 53505
Density	g/cm ³	1,17	DIN EN ISO 1183-1-A
Tensile strength	MPa	14	DIN 53504-S2
Elongation at break	%	1300	DIN 53504-S2
Tear strength	N/mm	40	DIN ISO 34-1Bb
Compression set at room temperature	%	25	DIN ISO 815
Compression set at 70 °C	%	35	DIN ISO 815
Compression set at 100 °C	%	50	DIN ISO 815

Test plaques are manufactured by injection moulding from pre-dried granules (water content of ≤0,02%). Test plaques are aged 20 hrs at 100°C. Specimens are cut from test plaques. Test conditions: 23°C ± 2°C and 50% ± 6% rel. humidity.

These are general guidance data. No statement regarding specific properties. All supplies are subject to detailed specifications to be agreed-up in each individual case and containing, among others, the tolerances to be specified therein.

General product information

Elastollan® LP 9277

®= Registered Trademark of Elastogran GmbH

Elastogran



■ • BASF Group

Storage and handling:

Elastollan® is hygroscopic, therefore storage in dry conditions and original container is recommended. Further information about drying, processing temperatures and post-treatment are given in our product brochure „Thermoplastic Polyurethane Elastomers (TPU) Elastollan®- Processing Recommendations“.

Chemical Characteristics:

Polymer based on: polyurethane, stabilizing agents and additives

Delivery form and packing:

Lentil shaped pellets
Bags, 25 kg net
Oktabins with PE liner bags, 1000 kg net

Processing:

Processable at least for 6 months from delivery date in original sealed containers with cool dry storage.

Hazard indication:

No particular hazards known.
Please look at the Material Safety Data Sheet before handling.

Waste Disposal:

More detailed information is provided in our country-specific information and the Material Safety Data Sheet.

Important Information:

There are national and international laws and regulations to consider if it is intended to produce consumer articles (e.g. articles that necessitate food or skin contact, toys etc.) or medical objects from Elastogran products. Where specific regulations do not exist, the current legal requirements of the European Union for consumer articles as well as medical products should be used as reference. Consultation with the Elastogran Sales Office and our Ecology and Product Safety Department is strongly recommended.

The data contained in this document shall constitute the agreed contractual quality of the product at the time of passing of risk. The data is reviewed at regular intervals as part of our quality assurance program. Neither this data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or fitness for a specific purpose. No liability may therefore be derived from the data contained herein.

如有疑问，请联系我们的销售部门
深圳市传佳新材料有限公司
深圳市光明新区别墅路1号世峰大厦1101
电话: 0755-81799887 , 林小姐18118772075
网址: <http://www.cjbase.com/>