



General product information

Elastollan® 1185 A 10HFFR

® = registered trademark of BASF Polyurethanes GmbH

PROPERTY	UNIT	STANDARD	VALUE
Hardness	Shore A	DIN 53505	86
Density	g/cm ³	DIN 53479	1.42
Tensile strength	MPa	DIN 53504	25
Elongation at break	%	DIN 53504	550
Oxygen index	Vol.-%	ISO 4589-1 / -2	30

*Please be informed that the value in above table is only representative values, not specification.

Date: Jan. 2011

THE INFORMATION SUBMITTED IN THIS PUBLICATION IS BASED ON OUR CURRENT KNOWLEDGE AND EXPERIENCE. IN VIEW OF MANY FACTORS THAT MAY AFFECT PROCESSING AND APPLICATION, THESE DATA DO NOT RELIEVE PROCESSORS FROM THE RESPONSIBILITY OF CARRYING OUT THEIR OWN TESTS AND EXPERIMENTS; NEITHER DO THEY IMPLY ANY LEGALLY BINDING ASSURANCE OF CERTAIN PROPERTIES OR OF SUITABILITY FOR A SPECIFIC PURPOSE. IT IS THE RESPONSIBILITY OF THOSE TO WHOM WE SUPPLY OUR PRODUCTS TO ENSURE THAT ANY PROPRIETARY RIGHTS AND EXISTING LAWS AND LEGISLATION ARE OBSERVED.